

# Technical Data Sheet

## Eastman Tritan™ Copolyester MX711

### Applications

- Blood contact and dialysis
- Blood tubes
- Fluid administration
- Medical devices
- Medical equipment
- Medical labware

### Key Attributes

- Excellent clarity
- Excellent hydrolytic stability
- Fast cycle times
- Fast drying times
- Good chemical resistance
- Good color stability upon ETO sterilization
- Good color stability upon gamma sterilization
- Good heat resistance
- Improved processability over traditional copolyesters
- Outstanding impact resistance

### Product Description

Eastman Tritan™ MX711 copolyester is an amorphous product with excellent appearance and clarity. Tritan MX711 contains a mold release derived from vegetable based sources. Tritan MX711 has many outstanding features that include excellent toughness, hydrolytic stability, heat resistance, and chemical resistance. Tritan MX711 has been formulated for medical devices. Tritan MX711 has been tested for FDA/ISO 10993 and USP Class VI Biological Evaluation testing after Gamma and ETO sterilization.

### Typical Properties

Property <sup>a</sup>	Test Method <sup>b</sup>	Typical Value, Units <sup>c</sup>
<b>General Properties</b>		
Specific Gravity	D 792	1.18
Mold Shrinkage	D 955	0.005-0.007 mm/mm (0.005-0.007 in./in.)
<b>Mechanical Properties (ISO Method)</b>		
Tensile Strength @ Yield	ISO 527	43 MPa
Tensile Stress @ Break	ISO 527	58 MPa
Elongation @ Yield	ISO 527	7 %
Elongation @ Break	ISO 527	185 %
Tensile Modulus	ISO 527	1548 MPa
Flexural Modulus	ISO 178	1495 MPa
Flexural Strength	ISO 178	59 MPa
Izod Impact Strength, Notched		
@ 23°C	ISO 180	93 kJ/m <sup>2</sup>
@ -40°C	ISO 180	20 kJ/m <sup>2</sup>
<b>Mechanical Properties</b>		
Tensile Stress @ Yield	D 638	43 MPa (6200 psi)
Tensile Stress @ Break	D 638	53 MPa (7700 psi)
Elongation @ Yield	D 638	6 %
Elongation @ Break	D 638	210 %
Tensile Modulus	D 638	1550 MPa (2.25 x 10 <sup>5</sup> psi)
Flexural Modulus	D 790	1550 MPa (2.25 x 10 <sup>5</sup> psi)
Flexural Yield Strength	D 790	62 MPa (9000 psi)
Rockwell Hardness, R Scale	D 785	112
Izod Impact Strength, Notched		
@ 23°C (73°F)	D 256	980 J/m (18.4 ft·lbf/in.)
@ -40°C (-40°F)	D 256	110 J/m (2.1 ft·lbf/in.)

Impact Strength, Unnotched		
@ 23°C (73°F)	D 4812	NB
@ -40°C (-40°F)	D 4812	NB
Impact Resistance (Puncture), Energy @ Max. Load		
@ 23°C (73°F)	D 3763	61 J (45 ft·lbf)
@ -40°C (-40°F)	D 3763	66 J (49 ft·lbf)
<b>Optical Properties</b>		
Total Transmittance	D 1003	90 %
Haze	D 1003	<1 %
<b>Thermal Properties</b>		
Deflection Temperature		
@ 0.455 MPa (66 psi)	D 648	99 °C (210 °F)
@ 1.82 MPa (264 psi)	D 648	85 °C (185 °F)
<b>Typical Processing Conditions</b>		
Drying Temperature		88 °C (190 °F)
Drying Time		4-6 hrs
Processing Melt Temperature		260-282 °C (500-540 °F)
Mold Temperature		38-66 °C (100-150 °F)

<sup>a</sup>Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup>Unless noted otherwise, the test method is ASTM.

<sup>c</sup>Units are in SI or US customary units.

## Technical Disclaimer

Eastman makes no representation and disclaims any warranty that the material in any particular shipment will conform exactly to the values given. Values as well as the performance of the final molded article may be affected by various factors such as the part design, mold design or tooling, drying, processing conditions as well as coloring or pigmentation of the product. No warranty of merchantability or fitness for use is made, and nothing herein waives any of the Seller's conditions of sale. You must make your own determination of the suitability of this product in your specific application due to the many factors (e.g. design, processing and conditions of use) that affect the performance of the final molded article. Suitability of use should be evaluated with appropriate testing and analysis. The processing melt temperature and mold temperature refer to the actual resin melt temperature and actual mold surface temperature respectively. Consider overall resin residence time, part shot size utilization and part geometry to set appropriate processing melt temperature and mold temperature in order to minimize IV loss and maximize molded part performance.

## Comments

Properties reported here are based on limited testing. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

---

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

9/12/2019 11:49:16 AM